

BOLPHANE

RENEW REDUCE RECYCLE

B-Nat® F


Ultrathin display shrinkfilm on the basis of a green polyethylene, high toughness crosslinked

Polyethylene from used cooking oil.

It consists of **20%** of a polyethylene produced from used cooking oil according to a mass balance management, **certified ISCC+**.

Besides coming from a renewable natural source, this green PE provides the same performances as a fossil polyethylene.

- Exceptional mechanical resistance to assure protection and product integrity.
- Easy to seal and shrink and compatible with a wide variety of packaging equipments.
- Combines toughness and softness. Adapts to the most demanding shapes and configurations.
- Good optic for best shelf appearance.
- Recyclable, contributes to minimising the carbon footprint.





Options for disposal are recycling (compatible with SPI code 4/PE-LD), incineration with energy recovery and landfill. Treatment, storage, transportation, and disposal must be in accordance with applicable federal, state/provincial and local regulations.

Food contact

Complies with EU and US regulations on food contact materials. See the « Declaration of Conformity » of concerned film reference for details.

Film storage

The maximum temperature for storage is 32° C, with a maximum of 80% RH, up to one year.











BOLLOR

INNOVATIVE

PACKAGING SHRINK FILMS





RENEW REDUCE RECYCLE

B-Nat® F

Technical Specifications

Technical properties	Test unit	Test Method	Values	
Reference			BNAT-F-15	
Presentation				
Grade			15	
Roll Length- Singlewound (S)	m		2 670	
Roll Length- Centerfolded (C)	m		1 335	
Width - Singlewound (S)	mm	mini : 150 - maxi : 1 400 - increment : 5		
Width - Centerfolded (C)	mm	<u>mini</u> : 150 - <u>maxi</u> : 1 000 - <u>increment</u> : 50		
Friction coefficients (film to fi	lm)			
Static		ASTM D1894	0.25	
Dynamic		ASTM D1894	0.18	
Optical properties				
Haze	%	ASTM D1003-A	4.0	
Gloss at 20°		ASTM D2457	120	
Shrinkage properties			LD*	TD*
Free shrink at 93°	%	ASTM D2732	12	17
Free shrink at 120°	%	ASTM D2732	78	78
Shrink force	kg/cm²	NFT 54-125	25	30
Mechanical properties	-		LD*	TD*
Stiffness modulus	Мра	ASTM D882	380	380
Elongation at break	%	ASTM D882	130	135
Tensile strength	Kg/cm ²	ASTM D882	1 600	1 600
Barrier properties				
	g/m²/24h		6 17	
Water vapor transmission rate	38°C, 95% HR	ASTM E96		
Oxygen transmission rate	cm ³ /m ² /24h 23°C, 0% HR	ASTM D3985	10 700	
* LD = Longitudinal Direction	Characteristics are those of a non-perforated film			





* TD = Transversal Direction

